CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Lab No.: CQCE/BBMP/SKSIPL/W.No.17/2017-18 02.04.2018

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

Client	: **Executive Engineer,** Rajarajeshwari Nagara Division, BBMP, Bangalore.
Agency	: **Sri. B.N Girish** **SKS Infrastructure Pvt. Ltd.** #180, K.G Nagar, 1st Main Road, Bangalore-560019.
Name of the work	: Construction of Dhyana Mandira at JP Park Phase II in Ward No.17.
Reference	: EE/RRND/Wo. No/000074/2017-18 dated:08.02.2018
Sample ID	: Cement Concrete - Lintel
Size of cubes	: 150mmx150mmx150mm
Cross Sectional Area	: 22500 mm^2
Technical Reference	: IS: 516-1959 (Reaffirmed 2008)
Grade of Concrete	: M_{25}
Compressive Strength as on	: 28^{th} day

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	05.03.2018	02.04.2018	8.365	628.9	27.95
2	05.03.2018	02.04.2018	8.348	614.5	27.31
3	05.03.2018	02.04.2018	8.382	639.1	28.40

Note:
1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಯಶವಂತಪುರ ಉಪ ವಿಭಾಗ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ

Office & Laboratory : # 133, Bhuvaneshwarinagar, Dodda Basti Main Road, Bangalore - 560 056.
e-mail:civilqualityconsultants@gmail.com Ph: 080-23240644 / Mob: 8553518550

Scanned by CamScanner

CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Job No.: CQCE/BBMP/SKSIPL/W.No.17/2017-18

14.03.2018

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

Client	: **Executive Engineer,** Rajarajeshwari Nagara Division, BBMP, Bangalore.
Agency	: **Sri. B.N Girish** **SKS Infrastructure Pvt. Ltd.** #180, K.G Nagar, 1st Main Road, Bangalore-560019.
Name of the work	: Construction of Dhyana Mandira at JP Park Phase II in Ward No.17.
Reference	: EE/RRND/Wo. No/000074/2017-18 dated:08.02.2018
Sample ID	: Cement Concrete - Deck slab
Size of cubes	: 150mmx150mmx150mm
Cross Sectional Area	: 22500 mm^2
Technical Reference	: IS: 516-1959 (Reaffirmed 2008)
Grade of Concrete	: M_{25}
Compressive Strength as on	: 7^{th} day

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	07.03.2018	14.03.2018	8.259	394.5	17.53
2	07.03.2018	14.03.2018	8.236	410.5	18.24
3	07.03.2018	14.03.2018	8.228	421.7	18.74

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಯಶವಂತಪುರ ಉಪ ವಿಭಾಗ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ

Office & Laboratory : # 133, Bhuvaneshwarinagar, Dodda Basti Main Road, Bangalore - 560 056.
e-mail:civilqualityconsultants@gmail.com Ph: 080-23240644 / Mob: 8553518550

Scanned by CamScanner

CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Job No.: CQCE/BBMP/SKSIPL/W.No.17/2017-18

04.04.2018

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

Client	: **Executive Engineer,** Rajarajeshwari Nagara Division, BBMP, Bangalore.
Agency	: **Sri. B.N Girish** **SKS Infrastructure Pvt. Ltd.** #180, K.G Nagar, 1st Main Road, Bangalore-560019.
Name of the work	: Construction of Dhyana Mandira at JP Park Phase II in Ward No.17.
Reference	: EE/RRND/Wo. No/000074/2017-18 dated:08.02.2018
Sample ID	: Cement Concrete - Deck slab
Size of cubes	: 150mmx150mmx150mm
Cross Sectional Area	: 22500 mm^2
Technical Reference	: IS: 516-1959 (Reaffirmed 2008)
Grade of Concrete	: M_{25}
Compressive Strength as on	: 28^{th} day

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	07.03.2018	04.04.2018	8.385	629.5	27.98
2	07.03.2018	04.04.2018	8.339	609.2	27.08
3	07.03.2018	04.04.2018	8.345	634.5	28.20

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಯಶವಂತಪುರ ಉಪ ವಿಭಾಗ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ

Office & Laboratory : # 133, Bhuvaneshwarinagar, Dodda Basti Main Road, Bangalore - 560 056.
e-mail:civilqualityconsultants@gmail.com Ph: 080-23240644 / Mob: 8553518550

Scanned by CamScanner